



RGD720

TRANSPARENT MATERIAL SIMULATING STANDARD PLASTICS

	ASTM	UNITS	METRIC	UNITS	IMPERIAL
Tensile Strength	D-638-03	MPa	50-65	psi	7250-9450
Elongation at Break	D-638-05	%	15-25	%	15-25
Modulus of Elasticity	D-638-04	MPa	2000-3000	psi	290,000-435,000
Flexural Strength	D-790-03	MPa	80-110	psi	12000-16000
Flexural Modulus	D-790-04	MPa	2700-3300	psi	390,000-480,000
HDT, °C @ 0.45MPa	D-648-06	°C	45-50	°F	113-122
HDT, °C @ 1.82MPa	D-648-07	°C	45-50	°F	113-122
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/inch	0.375-0.562
Water Absorption	D-570-98 24hr	%	1.5-2.2	%	1.5-2.2
Tg	DMA, E»	°C	48-50	°F	118-122
Shore Hardness (D)	Scale D	Scale D	83-86	Scale D	83-86
Rockwell Hardness	Scale M	Scale M	73-76	Scale M	73-76
Polymerized Density	ASTM D792	g/cm3	1.18-1.19		
Ash Content	USP281	%	0.01-0.02	%	0.01-0.02